

SPECIFICATION

AS
Zinc Plated Steel : JIS G3101

Item No. รหัสสินค้า	*Recommend Tensile kN แรงดึง	*Recommend Shear kN แรงเฉือน	Thread size ขนาดเกลียว "A"	Anchor Length ความยาวทั้งตัว "L" mm.	Pcs./Box ตัว/กล่อง	Pcs./Ctn. ตัว/ลัง
AS 8110	4.6	2.8	M 8	110	80	800
AS 10130	7.3	4.4	M 10	130	50	500
AS 12160	10.7	6.4	M 12	160	20	200
AS 16190	20.4	12.0	M 16	190	15	75
AS 20240	31.3	18.8	M 20	240	-	60
AS 24290	43.2	25.9	M 24	290	-	40
AS 27340	56.9	34.2	M 27	340	-	30
AS 30380	64.2	41.5	M 30	380	-	15



SPECIFICATION

AS-HDG
Hot Dip Galvanized

Item No. รหัสสินค้า	*Recommend Tensile kN แรงดึง	*Recommend Shear kN แรงเฉือน	Thread size ขนาดเกลียว "A"	Anchor Length ความยาวทั้งตัว "L" mm.	Pcs./Box ตัว/กล่อง	Pcs./Ctn. ตัว/ลัง
AS 8110 - HDG	4.6	2.8	M 8	110	80	800
AS 10130 - HDG	7.3	4.4	M 10	130	50	500
AS 12160 - HDG	10.7	6.4	M 12	160	20	200
AS 16190 - HDG	20.4	12.0	M 16	190	15	75
AS 20240 - HDG	31.3	18.8	M 20	240	-	60
AS 24290 - HDG	43.2	25.9	M 24	290	-	40
AS 27340 - HDG	56.9	34.2	M 27	340	-	30
AS 30380 - HDG	64.2	41.5	M 30	380	-	15


AS



SPECIFICATION

AS-SUS
Stainless Steel : AISI 304

Item No. รหัสสินค้า	*Recommend Tensile kN แรงดึง	*Recommend Shear kN แรงเฉือน	Thread size ขนาดเกลียว "A"	Anchor Length ความยาวทั้งตัว "L" mm.	Pcs./Box ตัว/กล่อง	Pcs./Ctn. ตัว/ลัง
AS 8110-SUS	5.7	3.5	M 8	110	80	800
AS 10130-SUS	9.1	5.5	M 10	130	50	500
AS 12160-SUS	13.3	8.0	M 12	160	20	200
AS 16190-SUS	25.0	15.0	M 16	190	15	75
AS 20240-SUS	39.1	23.5	M 20	240	-	60
AS 24290-SUS	54.0	32.4	M 24	290	-	40
AS 27340-SUS	71.1	42.7	M 27	340	-	30
AS 30380-SUS	86.5	51.9	M 30	380	-	15



SPECIFICATION



AS-G 8.8
HIGH TENSILE STUD ANCHOR RODS

Item No. รหัสสินค้า	*Recommend Tensile kN แรงดึง	*Recommend Shear kN แรงเฉือน	Thread size ขนาดเกลียว "A"	Anchor Length ความยาวทั้งตัว "L" mm.	Pcs./Box ตัว/กล่อง	Pcs./Ctn. ตัว/ลัง
AS 8110-88	9.2	5.6	M 8	110	80	800
AS 10130-88	14.6	8.8	M 10	130	50	500
AS 12160-88	21.3	12.8	M 12	160	20	200
AS 16190-88	40.0	24.1	M 16	190	15	75
AS 20240-88	62.6	37.6	M 20	240	-	60
AS 24290-88	86.4	51.9	M 24	290	-	40
AS 27340-88	113.8	68.3	M 27	340	-	30
AS 30380-88	138.4	83.0	M 30	380	-	15

* แรงดึง (Tensile) และแรงเฉือน (Shear) เป็นค่าของเฉพาะตัวสตั๊ดแองเคอร์เท่านั้น ในการใช้งานกับผูกเคมี จะต้องพิจารณาแรงดึงถอน (Pull out Load) ของผูกเคมีประกอบด้วย โดยยึดค่าที่ต่ำกว่าเป็นหลัก